

USBN: 09/698735

Docket No.: 53494US017

- C2 5 #1. A pavement marking comprising:  
a binder having polyurea groups, wherein the binder is prepared from a coating composition comprising:  
one or more aliphatic secondary amines;  
one or more polyisocyanates;  
material selected from the group consisting of fillers, extenders, pigments, and combinations thereof; and  
reflective elements;  
wherein the coating has an open time of at least 30 seconds and a track-free time of no greater than about 5 minutes.

- C3 7 #5. A pavement marking comprising:  
a binder having polyurea groups, wherein the binder is prepared from a coating composition comprising:  
one or more aliphatic secondary amines;  
one or more polyisocyanates;  
material selected from the group consisting of fillers, extenders, pigments, and combinations thereof; and  
reflective elements;  
wherein the coating has a track-free time of no greater than about 5 minutes and a retained reflectivity of at least 100 mod/m<sup>2</sup>/lux after at least 2 years in use as longitudinal traffic markings as measured according to ASTM E 1710-95.

- C4 10 #6. A pavement marking comprising:  
a binder having polyurea groups, wherein the binder is prepared from a coating composition comprising  
one or more aliphatic secondary amines comprising an aspartic ester amine;  
one or more polyisocyanates;  
material selected from the group consisting of fillers, extenders, pigments, and combinations thereof; and  
reflective elements;  
wherein the coating has a track-free time of no greater than about 5 minutes.

USPN: 09/698735Docket No.: 53494US017

A version marked up to show changes made to the claim(s) relative to the previous version of the claim(s) is attached.